

TECHNICAL DATA SHEET (effective 20OCT20)

Armacell (OleTex[®]) BDN 200 Buns (Blocks)

Polymer: Polyethylene / EVA

Physical Property	Test Method	Unit	Value
Cell Structure	-	-	Closed cell
Color	-	-	Various
Compression Deflection 10%	ASTM D 3575 Suffix D	psi kPa	1.16 min 8 min
Compression Deflection 25%	ASTM D 3575 Suffix D	psi kPa	4.5 - 6.5 31 - 41
Compression Set (Room temp)	ASTM D 3575 Suffix B	%	40 max
Density	ASTM D 3575 Suffix W	lb/ft ³ kg/m ³	1.56 - 2.56 25 - 40
Elongation	ASTM D 3575 Suffix T	%	200 min
Flammability	FMVSS 302 @ 1/4" and thicker	mm/min	Pass
Tear Strength	ASTM D 3575 Suffix T	lb/in kN/m	8 min 1.4 min
Tensile Strength	ASTM D 3575 Suffix T	psi kPa	29 min 200 min
Thermal Stability	ASTM D 3575 Suffix S	%	3 max
Water Absorption	ASTM D 3575 Suffix L	lb/ft ² kg/m ²	0.1 max 0.5 max

All data and technical information are based on results achieved under typical application conditions. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. By ordering/receiving product you accept the Armacell General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these.

© 2020 Armacell OleTex[®] is a registered trademark of the Armacell Group.

For more information:
www.armacell.us
info.cf.us@armacell.com
 800-973-0490