

Technical Data

Volara[®] Type M

PRODUCT DEFINITION

Volara type M is a flexible closed-cell polyethylene foam that is crosslinked by means of a unique electron irradiation process.

This results in a continuous smooth surface foam material with a fine cell structure and excellent mechanical properties. Compared to Volara type A, Volara type M offers higher temperature resistance along with higher stiffness.



HEAT STABILITY UP TO
215°F



ROLL FORM UP TO
2500ft.



C CUSTOM
COLORS AVAILABLE

PRODUCT CHARACTERISTICS

- Excellent thermal insulation
- Excellent chemical resistance
- Good mechanical properties at low densities
- Good compression molding grade
- Laminates to 2" available

PRODUCT FORM

- Produced in roll form up to 2500 lineal feet
- Density: 2pcf to 6pcf
 - Thickness range: 0.031" to 0.420"
 - Width range to 80"

PRODUCT COLORS

- Standard colors are natural-white and black
- Custom colors are available on request

APPLICATIONS



Transportation
Industry



General
Industrial



Industrial
Tape



Recreation
& Leisure



Packaging
Dunnage



Aviation &
Aerospace



Medical Tape
& Healthcare

Michigan Location

Sekisui Voltek, LLC
17 Allen Avenue
Coldwater, MI 49036

www.SekisuiVoltek.com
Tel: (800) 544-2254
Fax: (517) 279-8562

Fine-celled, Irradiation cross-linked, Polyolefin Foam

Volara® M

TYPICAL PROPERTIES OF VOLARA M		
	3pcf	6pcf
Compression Strength / (ASTM D3575)		
(lb / sq-in) @ 25% compression	10	25
Tensile Strength / (ASTM D3575)		
(lb / sq-in) Machine Direction	96	196
(lb / sq-in) Cross-Machine Direction	70	147
Tensile Elongation / (ASTM D3575)		
(%) Machine Direction	146	199
(%) Cross-Machine Direction	114	127
Tear Resistance / (ASTM D3575)		
(lb / in) Machine Direction	14	32
(lb / in) Cross-Machine Direction	22	47
Compression Set / (ASTM D3575)		
% Original Thickness	23	15
Thermal Stability 3 Hour Test @ 180°F		
AVE MD%	-0.8	-0.8
AVE CD% Change	-0.4	-0.4

September, 2010

NOTE:

This data represented on this technical data sheet should be used as a guideline for product selection. This data is not intended to represent, replace or be used as a proxy for a specific productsales specification. The physical properties are averages based on limited production runs and are subject to change as additional data becomes available.